



上海舜力实业有限公司

化学式 Formula: (PrNd)_xO_y

分子量 Mol.wt. 666.29

规格 Specification:

QB/SHTG 2102-1012

牌号 Code		Pr-Nd:15/85	Pr-Nd:20/80	Pr-Nd:25/75	Pr-Nd:30/70
稀土总量 TREO	%	≥99	≥99	≥99	≥99
纯度与相关稀土杂质 Purity and Relative Re-impurities					
Pr ₆ O ₁₁ /REO	%	15 ± 2	20 ± 2	25 ± 2	30 ± 2
Nd ₂ O ₃ /REO	%	85 ± 2	80 ± 2	75 ± 2	70 ± 2
La ₂ O ₃ /TREO	%	0.1	0.1	0.1	0.1
CeO ₂ /TREO	%	0.1	0.1	0.1	0.1
Sm ₂ O ₃ /TREO	%	0.05	0.05	0.05	0.05
非稀土杂质 Non-RE-impurities					
Fe ₂ O ₃	%	≤0.3	≤0.3	≤0.3	≤0.3
SiO ₂	%	≤0.05	≤0.05	≤0.05	≤0.05
Al ₂ O ₃	%	≤0.05	≤0.05	≤0.05	≤0.05
CaO	%	≤0.05	≤0.05	≤0.05	≤0.05
SO ₄ ²⁻	%	≤0.05	≤0.05	≤0.05	≤0.05
Cl ⁻	%	≤0.05	≤0.05	≤0.05	≤0.05



- ◆ 说明: 为棕褐色粉末。易吸水吸气, 须存放在干燥处, 不得露天放置, 运输时严防淋雨受潮。
- ◆ 用途: 供深加工和玻璃、陶瓷、磁性材料等用。
- ◆ 重量: 1000公斤;
- ◆ 包装: 本产品通常包装为50kg或1000kg, 也可以按用户要求包装。
- ◆ Description: Brown powder, easily absorb water and air, shall be stored in a dry place not open place, to prevent rain and moisture transport.
- ◆ Uses: For the deep processing of glass, ceramics, magnetic materials.
- ◆ Batch Weight: 1000 Kg
- ◆ Packaging: The product is usually packaged for 50kg or 1000kg, the package can also be requested by the user.